


# DanPal-TI, S.A. de C.V.

CUBIERTAS TRASLUCIDAS DE ALTA CALIDAD.




## LAMINA ACANALADA

ESPESOR	ANCHO STD.	LARGO STD.	COLORES	TRANS. LUZ	RAD. MIN. CURV.
0.80 mm	1.26 mts. 1.30 mts.	11.00 mts.	Cristal Bronce Opalino	90% 47% Opaco	4.00 mts.



## LAMINA SOLIDA

ESPESOR	ANCHO STD.	LARGO STD.	COLORES	TRANS. LUZ	RAD. MIN. CURV.	FACTOR "U"
*3.00 mm *4.50 mm *6.00 mm 9.50 mm 12.70 mm	1.22 mts. 1.83 mts.	2.44 mts.	Cristal Gris Bronce	50/86% 50/84% 50/82% 50/79% 50/75%	0.30 mts. 0.45 mts. 0.60 mts. 0.95 mts. 1.27 mts.	1.05 1.01 0.96 0.88 0.82
* También en rollo (Ancho 1.93 mts.)						



## LAMINA SOLIDA BALISTICA

TIPO	ESPESOR	ANCHO STD.	LARGO STD.	COLORES	TRANS. LUZ	NIVEL PROTECC.
MP-750	19 mm	1.22 mts	2.44 mts.	Cristal	87% (cristal)	nivel B - I FEM
SP-1250	32 mm	1.52 mts.		Gris Bronce	67% (cristal)	nivel C - III FEM